

Technical Data Sheet

Date of Issue 11/10/2016

Rev. 06_10/02/2023

2020

Painter's Basic Masking Tape



FSC® C148644
The mark of responsible forestry



PEFC 18-32-126
PEFC Certified



Product Description

Painter's Basic, medium adhesion masking tape characterized by a regular crepe paper backing and a solvent borne rubber resin adhesive. Suitable for indoor applications, for masking operations in painting and building, and for non-critical bundling, holding, splicing, and labeling. FSC® and PEFC certified masking tapes available on demand.

Features

- Medium adhesion
- Regular paper for masking operations
- Good holding power
- Clean removal in warm environments without breaking
- Good contact on multiple surfaces
- Good paint anchorage
- Indoor removal time: 5 Days

Main Applications

- DIY and Professional masking, painting and building operations (no UV exposure recommended)
- Non – critical bundling, splicing and holding
- Temporary labeling and marking activities

Technical Data

	Metric	Imperial Units	Test Method
Total weight*	80 g/m2	80 g/m2	ISO 536
Total thickness*	110 µm	4.3 mils	Internal
MD tensile strength*	37 N/cm	21.1 Lbs/in	AFERA 5004/PSTC 131
MD elongation at break*	7 %	7 %	AFERA 5004/PSTC 131
Adhesion to steel plate*	1.9 N/cm	17.4 oz/in	AFERA 5001/PSTC 101
Service temperature	up to 55°C	up to 131°F	

Backing material

Saturated crepe paper

Type of adhesive

Natural rubber

*Typical value

Available colour



White



Yellow

Technical Information and Product Use

All technical information and data above mentioned are provided to the best of our knowledge on the basis of our practical experience. Figures shown refer to average values only, based on tests carried out in conditioned laboratory and are not valid for specification. The company reserves the right to modify or change the products at any time without notice. The accuracy or completeness of such information is not guaranteed. The technical information, suggestions and other statements contained in this document have been compiled for your guidance and usage. PPM Industries reminds the user of the products to make sure that the product is used as per the instructions and suggestions provided. It is the user's sole responsibility to determine the suitability of the product in actual application under specific conditions.

Storage and Shelf Life

Suggested storage in dry area away from direct sunlight temperature should range from 59°F / 15°C to 77°F / 25°C with max relative humidity of 50%. Tape and jumbo roll should be used respectively within 12 months and 6 months from date of shipment. PPM Industries does not take responsibility for the defective material if it is not stored and used in accordance with the conditions listed above.